THK Original Grease

AFG Grease

- ●Base oil: high-grade synthetic oil
- Consistency enhancer: urea-based



AFG Grease is a high-grade grease for ball screws that uses high-grade synthetic oil as its base and a urea-based grease as its consistency enhancer. This ensures that it has superior low heatgenerating properties, allowing for use over a wide temperature range—from low to high temperatures

[Features]

(1) Low heat generation

Since the viscous resistance is low, the grease generates only a minimal level of heat even during high-speed operation.

(2) Low torque properties

Features a low base oil kinematic viscosity, making it ideal for ball screws.

(3) Water resistance

AFG Grease is a highly water-resistant grease that is less vulnerable to softening and reductions in extreme pressure resistance due to moisture penetration.

[Representative Physical Properties]

| Item | | Representative value | Test method |
|--|------------|--------------------------|---------------|
| Consistency enhancer | | Urea-based | |
| Base oil | | High-grade synthetic oil | |
| Base oil kinematic viscosity: mm²/s (40°C) | | 25 | JIS K 2220 23 |
| Worked penetration (25°C, 60 W) | | 285 | JIS K 2220 7 |
| Mixing stability (100,000 W) | | 329 | JIS K 2220 15 |
| Dropping point: ℃ | | 261 | JIS K 2220 8 |
| Evaporation amount: mass% (99°C, 22 h) | | 0.2 | JIS K 2220 10 |
| Oil separation rate: mass% (100℃, 24 h) | | 0.5 | JIS K 2220 11 |
| Copper plate corrosion (B method, 100°C, 24 h) | | Accepted | JIS K 2220 9 |
| Low-temperature torque: mN·m (-20°C) | Starting | 170 | JIS K 2220 18 |
| | Rotational | 70 | |
| 4-ball testing (welding load): N | | 3089 | ASTM D2596 |
| Service temperature range: °C | | -45 to 160 | |
| Color | | Brown | |



Českolipská 9, 412 01 Litoměřice




Telefon: +420 416 711 333 o.z. LIN-TECH HENNLICH s.r.o. E-mail: lin-tech@hennlich.cz

Lubrication

AFG Grease

[Low Heat Generation Test Data]







[Ball Screw Torque Data]

Test conditions Item Description SBN3210-7RRG0+1094LC5 Tested model (Pre-load only) Rotational speed 2 to 1200 min⁻¹ Amount of lubricant 13 cm3 (initial lubrication only) injected 2.0 AFG Grease 1.8 ----AFB-LF Grease Torque measurement result (N·m) 1.6 1.4 1.2 1.0 0.8 0.6 0.4 0.2 0.0 200 400 600 800 1000 1200 Rotational speed (min⁻¹)

