

Product: iglidur[®] A200

19.11.2013

General Properties:

density:	1.14 g/cm ³
colour:	white
saturation with moisture absorption at 23°C / 50% r. h.:	1.5 weight %
saturation with water:	7.6 weight %

Mechanical Properties:

flexural modulus:	2500 MPa
flexural strength:	116 MPa
max. permissible surface pressure at 20 °C:	18 MPa
Shore D hardness:	81

Thermal Properties:

highest long term service temperature ¹⁾ :	80°C
highest short term service temperature ^{1), 2)} :	170°C
highest short term ambient temperature ^{1), 2)} :	200°C
lowest service temperature:	-40°C

Electrical Properties:

specific volume resistivity:	>10 ¹³ Ωcm
surface resistivity:	>10 ¹² Ω

¹⁾ relaxation possible

²⁾ without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties .

Erstellt: 19.11.2013/Dr. Ralf Selzer/ Entwicklung

F-2-0034-A

i:\gleitlager\vertrieb\lisa.schulze\i\iglidur a200 product data sheet2013.doc

Geändert:

Stand: A

Verteiler: Technisches Marketing, Entwicklung

Seite 1 von 1