

Product: iglidur® J

General Properties:

density:	1.49 g/cm ³
colour:	yellow
saturation with moisture absorption at 23°C / 50% r. h.:	0.3 weight %
saturation with water:	1.3 weight %

Mechanical Properties:

flexural modulus:	2400 MPa
flexural strength:	73 MPa
max. permissible surface pressure at 20 °C:	35 MPa
Shore D hardness:	74

Thermal Properties:

highest long term service temperature ¹⁾ :	90°C
highest short term service temperature ^{1), 2)} :	120°C
highest short term ambient temperature ^{1), 2)} :	140°C
lowest service temperature:	-50°C

Electrical Properties:

specific volume resistivity:	>10 ¹³ Ωcm
surface resistivity:	>10 ¹² Ω

¹⁾ relaxation possible

²⁾ without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.

Erstellt: 19.11.2013 / Dr. Ralf Selzer / Entwicklung
Geändert: 04.12.2019 / Björn Haag / Entwicklung
Verteiler: Technisches Marketing Energieketten und Gleitlager,
Entwicklung Energieketten und Gleitlager

I:\QS\Qmdok\Formular\Allgemein\Entwicklung\F-2-0105 Vorlage Werkstoffdatenblatt.dot

QS-Nr.: F-2-0105-C

Seite 1 von 1