

Product: iglidur® RW370 printed

General Properties:

density: ³⁾	1.34 g/cm ³
colour:	beige
saturation with moisture absorption at 23 °C / 50 % r. h.:	0.25 weight %
saturation with water:	1.2 weight %

Mechanical Properties: ³⁾

flexural modulus:	2177 / 1407 MPa ⁴⁾
flexural strength:	91.2 / 30.2 MPa ⁴⁾
max. permissible surface pressure at 20 °C:	45 MPa
Shore D hardness:	80

Thermal Properties:

highest long-term service temperature ^{1), 2)} :	170°C
highest short-term service temperature ^{1), 2)} :	190°C
highest short-term ambient temperature ^{1), 2)} :	200°C
lowest service temperature:	-50°C

Electrical Properties: ³⁾

specific volume resistivity	>10 ¹² Ωcm
surface resistivity:	>10 ¹² Ω

- ¹⁾ relaxation possible
- ²⁾ without additional load; no movement
- ³⁾ depending on 3D printer and printing parameters
- ⁴⁾ printed flat / upright

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.

Erstellt:	30.4.19 Niklas Eutebach	I:\QS\Qmdok\Formular\Allgemein\Entwicklung\F-2-0105 Vorlage Werkstoffdatenblatt.dot
Geändert:	04.12.2019 / Ralf Selzer / Entwicklung	QS-Nr.:
Verteiler:	Technisches Marketing Energieketten und Gleitlager, Entwicklung Energieketten und Gleitlager	Seite 1 von 1